

Coated woodfree paper

Fine paper

NIVIS SATIN

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
			90	100	115	130
Substance	ISO 536	g/m <sup>2</sup>	90	100	115	130
Caliper	ISO 534	µm	73	80	92	104
Bulk	ISO 534	cm <sup>3</sup> /g	0,81	0,80	0,80	0,80
Smoothness Bekk	ISO 5627	s	500	500	500	450
Gloss Gardner	ISO 8254-1	%	40 max	40 max	45 max	45 max
Whiteness	ISO 11475	%	121	121	121	121
Brightness ISO	ISO 2470 (D65)	%	97	97	97	97
Opacity ISO	ISO 2471	%	92,5	94	95	96

**Notes:** 220 AND 270 ON REQUEST - 220 E 270 SU RICHIESTA

Finishing **Satin**

Printing method **Sheet-fed offset**

Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Coated woodfree paper

Fine paper

NIVIS SATIN

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m <sup>2</sup>	150	170	200	220
Caliper	ISO 534	µm	120	136	165	185
Bulk	ISO 534	cm <sup>3</sup> /g	0,80	0,80	0,83	0,84
Smoothness Bekk	ISO 5627	s	450	400	350	350
Gloss Gardner	ISO 8254-1	%	45 max	45 max	45 max	45 max
Whiteness	ISO 11475	%	121	121	121	121
Brightness ISO	ISO 2470 (D65)	%	97	97	97	97
Opacity ISO	ISO 2471	%	97	98	98 min	98 min

**Notes:** 220 AND 270 ON REQUEST - 220 E 270 SU RICHIESTA

Finishing **Satin**

Printing method **Sheet-fed offset**

Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Coated woodfree paper

Fine paper

NIVIS SATIN

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m <sup>2</sup>	250	270	300	350
Caliper	ISO 534	µm	215	240	270	325
Bulk	ISO 534	cm <sup>3</sup> /g	0,86	0,89	0,90	0,93
Smoothness Bekk	ISO 5627	s	350	350	350	350
Gloss Gardner	ISO 8254-1	%	45 max	45 max	45 max	45 max
Whiteness	ISO 11475	%	121	121	121	121
Brightness ISO	ISO 2470 (D65)	%	97	97	97	97
Opacity ISO	ISO 2471	%	98 min	98 min	98 min	98 min

**Notes:** 220 AND 270 ON REQUEST - 220 E 270 SU RICHIESTA

Finishing **Satin**

Printing method **Sheet-fed offset**

Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Coated woodfree paper

Fine paper

NIVIS SATIN

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m <sup>2</sup>	400			
Caliper	ISO 534	µm	380			
Bulk	ISO 534	cm <sup>3</sup> /g	0,95			
Smoothness Bekk	ISO 5627	s	250			
Gloss Gardner	ISO 8254-1	%	45 max			
Whiteness	ISO 11475	%	121			
Brightness ISO	ISO 2470 (D65)	%	97			
Opacity ISO	ISO 2471	%	99 min			

**Notes:** 220 AND 270 ON REQUEST - 220 E 270 SU RICHIESTA

Finishing **Satin**

Printing method **Sheet-fed offset**

Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Coated woodfree paper

Fine paper

NIVIS GLOSS

Substance	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
			90	100	115	130
Substance	ISO 536	g/m2	90	100	115	130
Caliper	ISO 534	µm	68	75	84	93
Bulk	ISO 534	cm3/g	0,76	0,75	0,73	0,72
Gloss Gardner	ISO 8254-1	%	68	70	72	73
Whiteness	ISO 11475	%	119	119	119	119
Brightness ISO	ISO 2470 (D65)	%	94,5	94,5	94,5	95
Opacity ISO	ISO 2471	%	91	93	94,5	96

**Notes:** 80,220 AND 270 ON REQUEST - 80,220 E 270 SU RICHIESTA

Finishing **Gloss**

Printing method **Sheet-fed offset**

Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

Substance	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
			150	170	200	220
Substance	ISO 536	g/m <sup>2</sup>	150	170	200	220
Caliper	ISO 534	µm	108	122	146	163
Bulk	ISO 534	cm <sup>3</sup> /g	0,72	0,72	0,73	0,74
Gloss Gardner	ISO 8254-1	%	76	76	76	76
Whiteness	ISO 11475	%	119	119	119	119
Brightness ISO	ISO 2470 (D65)	%	95	95	95	95
Opacity ISO	ISO 2471	%	97	98	98	98 min

**Notes:** 80,220 AND 270 ON REQUEST - 80,220 E 270 SU RICHIESTA

Finishing **Gloss**

Printing method **Sheet-fed offset**

Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m <sup>2</sup>	250	270	300	350
Caliper	ISO 534	µm	187	205	235	275
Bulk	ISO 534	cm <sup>3</sup> /g	0,75	0,76	0,78	0,79
Gloss Gardner	ISO 8254-1	%	76	75	75	74
Whiteness	ISO 11475	%	119	119	119	119
Brightness ISO	ISO 2470 (D65)	%	95	95	95	95
Opacity ISO	ISO 2471	%	98 min	98 min	98 min	98 min

**Notes:** 80,220 AND 270 ON REQUEST - 80,220 E 270 SU RICHIESTA

Finishing **Gloss**

Printing method **Sheet-fed offset**

Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m2	400			
Caliper	ISO 534	µm	320			
Bulk	ISO 534	cm3/g	0,80			
Gloss Gardner	ISO 8254-1	%	74			
Whiteness	ISO 11475	%	119			
Brightness ISO	ISO 2470 (D65)	%	95			
Opacity ISO	ISO 2471	%	99 min			

**Notes:** 80,220 AND 270 ON REQUEST - 80,220 E 270 SU RICHIESTA

Finishing **Gloss**

Printing method **Sheet-fed offset**

Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.